





**KOLOVRAT, ČM s. r. o.**  
stylové dekorační látky  
391 55 Chýnov

**Základní technické údaje:**

<b>Druh:</b>	<b><u>ALABAMA G</u></b>		
<b>Určení:</b>	potahová tkanina		ČSN EN ISO
<b>Materiálové složení:</b>		75 % PE, 25 % VI	
<b>Šíře:</b>		150 cm	
<b>Hmotnost:</b>		500 g/m	
<b>Dostava osnovy / útku:</b>	osnova: útek:	70 nití / cm 25 nití / cm	
<b>Pevnost v tahu:</b>	osnova: útek:	2186 N 900 N	13934-1 13934-1
<b>Odolnost v oděru:</b>	Martindale:	12 000 otáček	12947-2
<b>Posuv nití ve švu:</b>	posuv osnovních nití: posuv útkových nití:	1,3 mm 1,6 mm	80 0842 80 0842
<b>Stálobarevnost:</b>	na světle: chemické čištění: v suchém otěru: v mokřem otěru: v praní:	4-5 4-5 4-5 4-5 4-5	105-B02 105-D01 105-X12 105-X12 105-C06
<b>Změna rozměrů: po praní:</b>	osnova: útek:	-1,0% -1,5%	25077 25077
<b>Změna rozměrů po chemickém čištění:</b>	osnova: útek:	-1,0% -1,0%	3175-1,2 3175-1,2
<b>Způsob ošetřování:</b>		šamponování 	
<b>Skupina namáhání potahu:</b>	1 – příležitostné použití v domácnosti		549-80-96
<b>Možné provedení:</b>	nešpinivé, nehořlavé, zatemňující zátěr (jen u větších množstvích)		
<b>Vzory a jejich opakování:</b>	<b>2158</b> bez vzoru		

Všechny vzory jsou chráněny autorskými právy.



TLF 381 297 011  
FAX 381 297 029  
E-Mail: [info@kolovrat.cz](mailto:info@kolovrat.cz)  
http:// [www.kolovrat.cz](http://www.kolovrat.cz)

IČO: 47252561  
DIČ: CZ47252561  
OR: Krajský soud České Budějovice, C 2213



**KOLOVRAT, ČM s. r. o.**  
*Glamorous Jacquard Fabrics*  
**CZ-391 55 Chýnov**

---

<b>Article:</b>	<b><u>ALABAMA G</u></b>	
<b>Applications:</b>	upholstery fabric	
<b>Composition:</b>		75 % PE, 25 % VI
<b>Width:</b>		150 cm
<b>Mass:</b>		500 g/m
<b>Yarn density:</b>	warp:	70 threads/cm
	weft:	25 threads/cm
<b>Tensile strength:</b>	warp:	2186 N
	weft:	900 N
<b>Abrasion thread breakage:</b>	Martindale:	12 000 cycles
<b>Seam slippage:</b>	warp direction:	1,3 mm
	weft direction:	1,6 mm
<b>Colour fastness:</b>	to light:	4-5
	to chemical cleanig:	4-5
	to dry rubbing:	4-5
	to wet rubbing:	4-5
	to washing:	4-5
<b>Maintenance:</b>		shampooing 
<b>Shrinkage after washing:</b>	warp:	-1,0 %
	weft:	-1,5 %
<b>Shrinkage after chemical:</b>		
<b>cleaning:</b>	warp:	-1,0 %
	weft:	-1,5 %
<b>Modifications:</b>	flame retardant, blackout, dirty repellent (larger quantities only)	
<b>Designs and repeats:</b>	<b>2158</b>	uni

All designs are protected by copyright.

TLF: +420 381 297 011  
FAX: +420 381 297 029  
E-Mail: [info@kolovrat.cz](mailto:info@kolovrat.cz)  
http:// [www.kolovrat.cz](http://www.kolovrat.cz)

Identification No.: 47252561  
VAT No.: CZ47252561  
Registration No.: České Budějovice, C 2213